

CLAIMS

1. An interlayer film for a laminated glass,
which contains a matrix resin, a liquid plasticizer,
5 acetyl acetone, alkali metal and at least one kind of metal
selected from the group consisting of magnesium and
alkaline earth metal, the content of the alkali metal being
20 to 120 ppm, the content of at least one kind of metal
selected from the group consisting of magnesium and
10 alkaline earth metal being 15 ppm or more and less than 60
ppm, and the content of the acetyl acetone being 0.008
parts by weight or more with respect to 100 parts by weight
of the matrix resin.
- 15 2. The interlayer film for a laminated glass
according to Claim 1,
wherein at least one kind of metal selected from the
group consisting of magnesium and alkaline earth metal is
magnesium.
- 20 3. A laminated glass,
which has the interlayer film for a laminated glass
according to Claim 1 or 2 and two glass plates supporting
the interlayer film for a laminated glass by sandwiching,
25 and has a metal coating layer in at least one interface of
two interfaces between the interlayer film for a laminated
glass and the glass plates.